



DIABLO



<i>Parametri standard</i>	<i>Unità di misura</i>	<i>Norma di riferimento</i>											
Grammatura	g/m2	ISO 536	60	70	80	90	100	120	140	170	190	250	300
Spessore	µm	ISO 534	79	91	103	115	125	144	164	201	223	298	346
Ruvidità Bendtsen	µm	ISO 8791-2	225	225	225	225	225	225	225	225	225	225	225
Opacità	%	ISO 2471	87	90	92	93	94	96	98	99	99	99	99
Bianco	%	ISO 2470	103,5	103,5	103,5	103,5	103,5	103,5	103,5	103,5	103,5	103,5	103,5
Bianco	%	ISO 11475	145	145	145	145	145	145	145	145	145	145	145