



PERGRAPHICA®



Technical Data: PERGRAPHICA High White Rough

Basis weight		g/m ²	ISO 536		90 ± 3.0
Caliper		µm	ISO 534		117 ± 3
Stiffness 15°/10mm	MD	mN	ISO 2493-1	min	150
Stiffness 15°/10mm	CD	mN	ISO 2493-1	min	70
Roughness Bendtsen		ml/min	ISO 8791-2		350 ± 100
Opacity		%	ISO 2471		93.5
Brightness UV		%	ISO 2470		109.0 ± 1.5
CIE Whiteness		%	ISO 11475		157 ± 3.0

Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001.
Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

typical shade values D65/10°: L*: 94.9 a*: 3.7 b*: -12.7 typical bulk: 1.30



PERGRAPHICA®



Technical Data: PERGRAPHICA High White Rough

Basis weight		g/m ²	ISO 536		240 ± 7.0
Caliper		µm	ISO 534		313 ± 7
Stiffness 15°/10mm	MD	mN	ISO 2493-1	min	1700
Stiffness 15°/10mm	CD	mN	ISO 2493-1	min	1000
Roughness Bendtsen		ml/min	ISO 8791-2		350 ± 100
Opacity		%	ISO 2471		99.5
Brightness UV		%	ISO 2470		109.0 ± 1.5
CIE Whiteness		%	ISO 11475		157 ± 3.0

Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001.
Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

typical shade values D65/10°: L*: 94.9 a*: 3.7 b*: -12.7 typical bulk: 1.30



PERGRAPHICA®



Technical Data: PERGRAPHICA High White Rough

Basis weight		g/m ²	ISO 536		100 ± 3.0
Caliper		µm	ISO 534		130 ± 3
Stiffness 15°/10mm	MD	mN	ISO 2493-1	min	190
Stiffness 15°/10mm	CD	mN	ISO 2493-1	min	90
Roughness Bendtsen		ml/min	ISO 8791-2		350 ± 100
Opacity		%	ISO 2471		94.5
Brightness UV		%	ISO 2470		109.0 ± 1.5
CIE Whiteness		%	ISO 11475		157 ± 3.0

Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001.
Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

typical shade values D65/10°: L*: 94.9 a*: 3.7 b*: -12.7 typical bulk: 1.30



PERGRAPHICA®



Technical Data: PERGRAPHICA High White Rough

Basis weight		g/m ²	ISO 536		150 ± 4.0
Caliper		µm	ISO 534		195 ± 5
Stiffness 15°/10mm	MD	mN	ISO 2493-1	min	550
Stiffness 15°/10mm	CD	mN	ISO 2493-1	min	330
Roughness Bendtsen		ml/min	ISO 8791-2		350 ± 100
Opacity		%	ISO 2471		97.5
Brightness UV		%	ISO 2470		109.0 ± 1.5
CIE Whiteness		%	ISO 11475		157 ± 3.0

Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001.
Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

typical shade values D65/10°: L*: 94.9 a*: 3.7 b*: -12.7 typical bulk: 1.30



PERGRAPHICA®



Technical Data: PERGRAPHICA High White Rough

Basis weight		g/m ²	ISO 536		300 ± 8.0
Caliper		µm	ISO 534		391 ± 8
Stiffness 15°/10mm	MD	mN	ISO 2493-1	min	2400
Stiffness 15°/10mm	CD	mN	ISO 2493-1	min	1500
Roughness Bendtsen		ml/min	ISO 8791-2		350 ± 100
Opacity		%	ISO 2471		99.5
Brightness UV		%	ISO 2470		109.0 ± 1.5
CIE Whiteness		%	ISO 11475		157 ± 3.0

Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001.
Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

typical shade values D65/10°: L*: 94.9 a*: 3.7 b*: -12.7 typical bulk: 1.30



PERGRAPHICA®



Technical Data: PERGRAPHICA High White Rough

Basis weight		g/m ²	ISO 536		120 ± 4.0
Caliper		µm	ISO 534		150 ± 3
Stiffness 15°/10mm	MD	mN	ISO 2493-1	min	300
Stiffness 15°/10mm	CD	mN	ISO 2493-1	min	170
Roughness Bendtsen		ml/min	ISO 8791-2		350 ± 100
Opacity		%	ISO 2471		96.5
Brightness UV		%	ISO 2470		109.0 ± 1.5
CIE Whiteness		%	ISO 11475		157 ± 3.0

Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001.
Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

typical shade values D65/10°: L*: 94.9 a*: 3.7 b*: -12.7 typical bulk: 1.30